



PYROBOR[®] Dehydrated Borax Coarse Grade

Brand Name: THREE ELEPHANT[®] PYROBOR[®] Dehydrated Borax
Chemical Name: Sodium tetraborate
Also known as: Anhydrous borax, borax glass, fused borax, dehydrated borax
Formula: Na₂B₄O₇
Molecular Weight: 201.22
CAS / TSCA No.: 1330-43-4 **REACH:** 01-21199490790-32-0001
Description: A free flowing mixture of clear, glass-like particles and white granules formed by the crushing of relatively large masses of fused materials.
Grades: Coarse



If you require guidance in developing product specifications, please contact Quality Assurance at (760) 372-2243

Properties

Chemical Analysis

	Specification
Boric Oxide (B ₂ O ₃)	68.5 % min
Equivalent Borax (Na ₂ B ₄ O ₇)	99.0 % min
Sodium Oxide (Na ₂ O)	30.5 % min
Sulfate (as SO ₄)	150 ppm max
Sodium Sulfate (as Na ₂ SO ₄)	223 ppm max
Total Iron (Fe)	≤ 50 ppm

Physical Analysis

U.S. Standard Sieve No.	Specification
<i>(% cum. retained)</i>	
+12	2 % max
+30	50 % min

Note: All data in the above specification are determined by Searles Valley Minerals analytical methods.

Packaging

Poly Bags: 25 kg
Semi-bulk Bags: 2,000 lb and 1,000 kg
Bulk: Hopper cars

Handling

Information concerning the handling and use of this product is provided in a safety data sheet (SDS). The SDS must be fully read and understood prior to any exposure, handling, or use of the product.

The information herein is believed to be reliable. However, no warranty, expressed or implied, is made as to its accuracy or completeness and none is made as to **MERCHANTABILITY** of the material or its **FITNESS FOR ANY PURPOSE**. The manufacturer shall not be liable for consequential damages or for damage to persons or property resulting from its use. Nothing herein shall be construed as a recommendation for use in violation of any patent.



RESPONSIBLE CARE[®]
OUR COMMITMENT TO SUSTAINABILITY



Searles Valley Minerals

Searles Valley Minerals
 13200 Main Street, Trona, CA 93562-1995
 P.O. Box 367, Trona, CA 93592-0367
 Sales/Service: 800.637.2775 / 913.344.9500

Theoretical Properties

The following properties are textbook theoretical data and are provided for convenience and reference only. These properties are not normally tested for the commercial product and no representation is made relative to the commercial product.

Theoretical Composition

Sodium oxide	(Na ₂ O)	30.8 %
Boric oxide	(B ₂ O ₃)	69.2 %

Stability

On exposure, anhydrous borax, PYROBOR®, slowly absorbs moisture, gradually reverting back to a hydrate. The clear, glassy particles become white and opaque.

Melting Point

742.5°C (1367°F)

Angle of Repose, *horizontal*

31 degrees

Specific Heat @ 25°C

44.64 cal/deg-mol

Other Information

PYROBOR® is completely anhydrous borax produced by the dehydration and fusion of decahydrate borax. On cooling, the fused product converts to an amorphous (glassy) form. The chemical equivalent of 100 pounds (or kilos) of decahydrate is contained 52.8 pounds (or kilos) of anhydrous borax.

Heat of Solution @ 18°C

7.26 Kcal/g-mol or 28.81 Btu

Heat of Formation @ 25°C

-786.6 Kcal/g-mol or -3121.6 Btu



RESPONSIBLE CARE
OUR COMMITMENT TO SUSTAINABILITY



Searles Valley Minerals

Searles Valley Minerals
13200 Main Street, Trona, CA 93562-1995
P.O. Box 367, Trona, CA 93592-0367
Sales/Service: 800.637.2775 / 913.344.9500